

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claims 1-10 (canceled)

Claim 11 (currently amended): A process for the decorative design of a surface of a motor vehicle or parts thereof, comprising the following steps:

- a) coating applying a surface of a motor vehicle or part thereof with a cationically and/or radically curable coating agent capable of being cured by high energy radiation onto the surface of the motor vehicle or parts thereof to be decorated to form an uncured coating layer, wherein the coating is applied to the surface of the motor vehicle or part thereof that is to be decorated,
- b) pressing one or more embossing dies exhibiting a relief having amplitude maxima that are spaced from one another in the range from 100 to 20,000 nm, into the uncured coating layer at a place or places to be decorated to form one or more regions that are covered by the one or more embossing dies, wherein the dies are partially or totally translucent to the high energy radiation,
- c) at least partially curing the regions that are covered by the one or more embossing dies by irradiation through the one or more embossing dies with high energy radiation, wherein the embossing dies are partially or totally translucent with respect to the high energy radiation,
- d) removing the one or more embossing dies, and
- e) curing the at least partially cured regions if necessary with high energy radiation to completely cure the at least partially cured regions.

Claim 12 (previously presented): The process according to claim 11 wherein said coating agent is capable of being cured by irradiation with light and said at least partial curing is effected by irradiation with light.

Claim 13 (previously presented): The process according to claim 12 wherein said irradiation is effected with light having a wavelength from 180 to 1,000 nm.

Claim 14 (previously presented): The process according to claim 11 wherein said coating agent is capable of being cured by thermal means, and wherein said at least partially curing of step (e) is thermal.

Claim 15 (previously presented): The process according to claim 11 wherein a transparent coating layer is applied before step (e).

Claim 16 (previously presented): The process according to claim 11 wherein a transparent coating layer is applied after step (e).

Claim 17 (canceled)

Claim 18 (currently amended): A motor vehicle or parts thereof with a decorative surface or partial surface formed by a process comprising the following steps:

- a) coating applying a surface of a motor vehicle or part thereof with a
cationically and/or radically curable coating agent capable of being cured
by high energy radiation ~~onto the surface of the motor vehicle or parts~~
~~thereof to be decorated~~ to form an uncured coating layer, wherein the
coating is applied to the surface of the motor vehicle or part thereof that is
to be decorated,
- b) pressing one or more embossing dies exhibiting a relief having amplitude
maxima that are spaced from one another in the range from 100 to 20,000
nm, into the uncured coating layer at a place or places to be decorated to
form one or more regions that are covered by the one or more embossing
dies, wherein the dies are partially or totally translucent to the high energy
radiation,
- c) at least partially curing the regions that are covered by the one or more
embossing dies by irradiation through the one or more embossing dies
with high energy radiation, wherein the embossing dies are partially or
totally translucent with respect to the high energy radiation,
- d) removing the one or more embossing dies, and

Se. No. 09/856,345
Docket No. FA 1010 US NA

- e) curing the at least partially cured regions if necessary with high energy radiation to completely cure the at least partially cured regions.

Claim 19 (canceled)

Claim 20 (previously presented): The substrate according to claim 18 wherein said coating agent is capable of being cured by thermal means, and wherein said at least partially curing of step (e) is thermal.